

Aquawood Primo A3

5453000310 ff

Water-based pigmented **wood preservative impregnation** for **wooden windows** and **front doors** for **industrial and professional use**

It has been matched as a system with a **3-coat structure**

PRODUCT DESCRIPTION

General

Water-based, pigmented ready-to-use wood preservative impregnation with biocidal active substances with particularly good coverage of softwood edges. The product is characterised by very good sagging behaviour on hardwood and softwood. Contains effective light stabilizers to absorb UV radiation and to stabilize the lignin component of the wood.

Special properties and standards

- Approval as a wood preservative (PT8) according to the Biocidal Products Directive of the EU.
- The active substances used provide the protection against blue stain (test according to DIN EN 152) and wood-destroying fungi (test according to EN 113) required by ÖNORM B 3803 and DIN 68800-3. Application quantity for testing in conformity with the standards 120-200 g/m².

Active substances (B, P, W)

8.0 g/kg (0,80 %) IPBC (Iodpropinylbutylcarbamat)

4,0 g/kg (0,40%) Tebuconazol

- Certificate of appreciation (05/93) ARGE Holzschutzmittel (wood preservatives consortium), Association of the Austrian chemical industry.
- **French ordinance DEVL1104875A** regarding the marking of construction coating products for their emission of volatile pollutants: A+




Application area



- For dimensionally stable and limited dimensionally stable timber components for exterior and interior use, such as wooden windows, front doors, window shutters, gates, winter gardens, in usage classes 2 and 3 without soil contact.

PROCESSING

Instructions for use



- Please stir the product before use. However, prevent entry of air while stirring.
- The temperature of the product and object, and the room temperature must be at least +15 °C.
- The optimal conditions for use are between 15 – 25 °C with a relative atmospheric humidity between 40 – 80 %.

03-20 (supersedes 02-20) ZKL 5453


ADLER-Werk Lackfabrik, A-6130 Schwaz

Phone: 0043/5242/6922-190, Fax: 0043/5242/6922-309, Mail: technical-support@adler-lacke.com

Our instructions for use are based on knowledge available currently and shall guide the buyer/user to the best of one's knowledge, but, however, must be clarified for the areas of application and processing conditions on a case-to-case basis. The buyer/user is responsible for deciding on the suitability and use of the delivered product, which is why it is recommended to produce a sample to check the suitability of the product. Our general terms and conditions of sale are otherwise applicable. All previous data sheets are rendered invalid with the issue of this one. Rights reserved for the modification of the container sizes, colour shades and degrees of gloss available.

- The treated surfaces must be coated with a suitable topcoat to prevent the active substances from being washed out. This surface coating must be maintained continuously.
- In case of flow coating for a long time, the pH-value reduces and, as a result, there could be sagging problems. Hence, the pH value of impregnations that have already been used must be checked and, if required, corrected to the target pH-value of 9.0 – 9.45 by adding 0.10 – 0.20 % of the neutralisation agent 96149 (the addition of 0.10 % will increase the pH-value up to approx. 0.6 units).
- If the viscosity increases as a result of evaporation, it must be compensated with water (set viscosity: 47 – 52 s (2-mm-cup) Before measuring the wood dust has to be screened.
- On foam generation in the flow-coating machine we recommend an addition of 0.2 – 0.3 % Entschäumerlösung 90642 oder ADLER Entschäumerlösung 90643.
- Please follow our **ARL 300 - Working guideline for coating dimensionally stable and limited dimensionally stable construction elements - General part** along with all standards and guidelines for window construction, **ARL 056 - Working guideline for the use of wood preservatives** and our **ARL 340 - Wood protection of dimensionally stable and limited dimensionally stable construction elements according to DIN 68800/1-3.**

Application technique



Application method	Immersion	Flow coating
Yield per application (g/m ²)	100 - 120	

Attention: Do not spray the product!

The product is ready to use.

The shape, the properties and moisture of the substrate affect the consumption/yield. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying times

(at 23 °C and 50 % rel. humidity)



Recoatable	after approx. 4 hours
Recoatable after forced drying: 20 min dripping 50 min drying stage (35– 40 °C) 20 min cooling stage	after approx. 90 minutes

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.


Avoid direct sunlight (very quick drying).

Cleaning the working equipment



With water immediately after use.

To remove dried paint residues we recommend using ADLER Aqua-Cleaner 80080 (diluted 1:1 with water).

SUBSTRATE																									
Type of substrate	Wood in accordance with the guidelines for window construction.																								
Substrate property	The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating. A prerequisite for ensuring long durability of the coating is to observe the basic principles of constructional wood preservation.																								
Wood moisture	13 % +/- 2 %																								
Wood sanding:	Hardwoods: grit size 150 – 180 Softwoods: grit size 100 – 150																								
COATING SYSTEM																									
General	The following coating systems are exemplary.																								
Impregnation	1 x Aquawood Primo A3 5453000310 ff																								
Intermediate coat	1 x Aquawood Intermedio 53663 or 1 x Aquawood Intermedio ISO 53613 Intermediate drying: approx. 2 hours Please observe the relative technical data sheets of the products.																								
Intermediate sanding	Grit size 220 - 240 Remove sanding dust.																								
																									
Finishing coat	1 x Aquawood DSL Q10 M 51751 ff or 1 x Aquawood DSL HighRes 59127 ff Please observe the relative technical data sheets of the products.																								
For front doors:	An additional application of Aquawood Protect 53215 is necessary (colourless two-component varnish). Please observe the relative technical data sheets of the products.																								
ORDERING INFORMATION																									
Size of trading unit	4 l, 22 l, 120 l poly-drum																								
Colour shades / degrees of gloss	<table> <tbody> <tr><td>Hellbraun</td><td>5453000310</td></tr> <tr><td>Kiefer</td><td>5453000311</td></tr> <tr><td>Linde</td><td>5453000312</td></tr> <tr><td>Altholz</td><td>5453000313</td></tr> <tr><td>Eiche geräuchert U</td><td>5453000321</td></tr> <tr><td>Schwarz</td><td>5453000330</td></tr> <tr><td>Lehm</td><td>5435000332</td></tr> <tr><td>Treibholz</td><td>5453000345</td></tr> <tr><td>Eiche U</td><td>5453000350</td></tr> <tr><td>Lärche U</td><td>5453000351</td></tr> <tr><td>Eiche Mittel U</td><td>5453000353</td></tr> <tr><td>Walnuss U</td><td>5453000354</td></tr> </tbody> </table>	Hellbraun	5453000310	Kiefer	5453000311	Linde	5453000312	Altholz	5453000313	Eiche geräuchert U	5453000321	Schwarz	5453000330	Lehm	5435000332	Treibholz	5453000345	Eiche U	5453000350	Lärche U	5453000351	Eiche Mittel U	5453000353	Walnuss U	5453000354
Hellbraun	5453000310																								
Kiefer	5453000311																								
Linde	5453000312																								
Altholz	5453000313																								
Eiche geräuchert U	5453000321																								
Schwarz	5453000330																								
Lehm	5435000332																								
Treibholz	5453000345																								
Eiche U	5453000350																								
Lärche U	5453000351																								
Eiche Mittel U	5453000353																								
Walnuss U	5453000354																								

Supplementary products

Aquawood Intermedio 53663
 Aquawood Intermedio ISO 53613
 Aquawood DSL Q10 M 51751 fff
 Aquawood DSL HighRes 59127 ff
 Aquawood Protect 53215
 ADLER Aqua-Cleaner 80080
 ADLER Neutralisationsmittel 96149
 ADLER Entschäumerlösung 90642
 ADLER Entschäumerlösung 90643

FURTHER DETAILS**Durability / storage**

At least 1 year in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Technical specifications

Delivery viscosity	approx. 47 - 52 s in accordance with DIN 53211 (2-mm-cup, 20 °C)
VOC content	EU threshold for Aquawood Primo A3 (cat. A/f): 130 g/l (2010). Aquawood Primo A3 contains a maximum of 80 g/l VOC.

Safety-related information

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.

The product is only suitable for the industrial and professional use

Use wood preservatives safely. Always read the label and observe the relative technical data sheets of the products before use.

Wood freshly treated with Aquawood Primo A3 must be stored on an impermeable, hard substrate after painting to prevent product residue from penetrating into the ground or waters. Any leaking product must be collected for reuse or disposal.

Aquawood Primo A3 contains active biocidal substances to protect against blue stain and wood-destroying fungi. The product should therefore only be used when protection of the wood is prescribed or in specific cases when it is necessary. Do not apply in rooms which are used to gain, produce, store or sell food and feed. Do not use for wood that is fitted in apiaries or saunas and for wood in permanent contact with the ground and/or waters. Danger for bats. Treated wood is not to be used within spitting distance to waters.